Work Order	3109.1_Rev1
Setup-Code	180611-10290-2801-01

Test Report

JIS Z 2801:2012 (Mod)

Antimicrobial products – Test for antimicrobial activity and efficacy

Test Object:

Coated Leneta-Foil vs. E. coli DSM 1576

Work Order	3109.1_Rev1
Setup-Code	180611-10290-2801-01

Report on Findings

Client: NANO4LIFE EUROPE L.P.
Address: Vouliagmenis Ave. 318
Ag. Dimitros – 173 43
Athens/Greece

Work order no.: 3109.1_Rev1

Test object: Coated Leneta-Foil vs. E. coli DSM 1576

Sample description: Coated Foil

Date of receipt of sample: 08.06.2018

Type of test: JIS Z 2801:2012 Antimicrobial products – Test for antimicrobial activity and efficacy

Test Germ: Escherichia coli DSM1576 ATCC8739 ISML CC 02/023

Test laboratory: QualityLabs BT GmbH

Address: Neumeyerstrasse 46a
90411 Nuremberg, Germany

Setup-Code: 180611-10290-2801-01

Sample material: Leneta-Foil

No. of pages in report: 7

Report on findings to the client:
Place and date of preparation: Nuremberg, 17.9.2018
Recipient: NANO4LIFE EUROPE L.P.
Revision of the sample report from 14.9.2018

Laboratory Director:

Harald Gerauer, Laboratory Director
QualityLabs BT GmbH

Released:

Markus Zehe, Managing Director
QualityLabs BT GmbH

Declaration on Quality Assurance

This investigation was performed and supervised according to the standard operating procedure “SOP zu JIS Z 2801:2012 (Mod)" by QualityLabs BT GmbH. The laboratory and process are continually monitored by independent, external authorities, as well as by internal audits.

Archiving

A copy of the test report, a protocol of the measurement as well as the accompanying correspondence and business records are archived by QualityLabs BT GmbH. The retention period is at least 10 years.

Test description

Anti-bacterial activity is determined in accordance with a modified version of JIS Z 2801:2012.

During the test, a thin liquid-film containing the bacteria (1.25×10^4 CFU / cm^2) is applied directly to the test sample (Standard: 5 cm x 5 cm). To avoid desiccation a foil (Standard: 4cm x 4cm, Stomacher Bags) is applied. Immediately after inoculation, the bacteria from the reference sample are separated from the sample and the enveloping foil surfaces using ultrasound and vortex devices and the number of viable germs (CFU – colony-forming units) is determined (t_0 value). A further set of reference samples and samples given anti-microbial treatment is incubated with bacteria in a liquid-film and the enveloping foil in a damp environment at 37°C. After 24 hours, the bacteria are separated from the sample surfaces using ultrasound and vortex devices and the number of viable germs is determined (t_{24} value).

Assessment of antimicrobial activity

A logarithmic germ reduction of **≥ 3 log scales** of the antimicrobial sample in comparison to the respective reference is used as assessment criterion to pass the antimicrobial test.

Germ reduktion [log scales]	Antibacterial activity
< 3	Not sufficient antimicrobial activity
≥ 3	Sufficient antimicrobial activity

References to Testconditions

Testconditions		
Sample size	25	cm^2
Foil size	16	cm^2
Volume Inoculum	400	µl
Sample cleaning	Isopropanol	-

References to deviations, preincubations, special test conditions

NONE

Work Order	3109.1_EN
Setup-Code	180611-10290-2801-01

Test Results

	Sample Name	Sample Code	t_0 (cells/cm^2)			t_{24} (cells/cm^2)			Reduction [%]	Log Reduction
1	Leneta-Folie P121-10 (Reference)	102900806180001	9.0 x 10^4	1.1 x 10^5	1.1 x 10^5	5.1 x 10^5	4.1 x 10^5	5.3 x 10^5	-	-
2	NANO4-CLEAN/PRIME NANO4-HYGIENE LIFE	102900806180002				< 1.0 x 10^1	< 1.0 x 10^1	< 1.0 x 10^1	**> 99.99**	**> 4**

*see “Interpretation of Results”, page 6

Test strain	*Escherichia coli DSM1576 ATCC8739 ISML CC 02/023*
Initial cell count inoculum / cm^2	**1.25 x 10^4**
Initials of the editor	JJ
Measurement ended on	Jun-15-2018

Work Order	3109.1_EN
Setup-Code	180611-10290-2801-01

Comments on test objects

NONE

Interpretation of the results based on the measurements

NONE

Editor: Mrs. Jovanovic ____ **Crosschecked:** Mr. Shendi____

References

JIS Z 2801:2012 Antimicrobial products – Test for antimicrobial activity and efficacy